

Cross-linking Peroxides / Crosslinked EVA

Product Name	Chemical Description	Chinese Name	Cas #	XL Temperature (°C)	Safe Processing Temperature (°C)	Active Oxygen
DPIB-40A-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% on EVA	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于EVA中	25155-25-3	175	135	3.8
DPIB-40B-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DCP-40A-gr	Dicumyl peroxide, granules, 40% on EVA	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-FF	Dicumyl peroxide, crystalline powder	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	5.86