

**Cross-linking Peroxides / Crosslinked PBD Rubber**

Product Name	Chemical Description	Chinese Name	Cas #	XL Temperature (°C)	Safe Processing Temperature (°C)
CH335-40B-gr	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, granules, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 细小颗粒,40%添加于中性填料中	6731-36-8	160	125
CH335-40B-pd	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, powder, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 粉状,40%添加于中性填料中	6731-36-8	160	125