

Cross-linking Peroxides / Crosslinked EPDM

Product Name	Chemical Description	Chinese Name	Cas #	XL Temperature (°C)	Safe Processing Temperature (°C)	Active Oxygen
DPIB-40B-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40B-gr-dd★	Di(tert-butylperoxyisopropyl)benzene, granules dedusted, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 脱尘细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40B-pd★	Di(tert-butylperoxyisopropyl)benzene, powder, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 粉状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40K-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40K-pd★	Di(tert-butylperoxyisopropyl)benzene, powder, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 粉状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40MB-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40MB-sl★	Di(tert-butylperoxyisopropyl)benzene, slabs, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 块状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-fl★	Di(tert-butylperoxyisopropyl)benzene, flakes	双(叔丁基过氧化异丙基)苯 片状	25155-25-3	175	135	9.08
DCP-40B-gr-dd	Dicumyl peroxide, granules dedusted, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40B-pd	Dicumyl peroxide, powder, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40K-gr	Dicumyl peroxide, granules, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40K-pd	Dicumyl peroxide, powder, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40MB-gr	Dicumyl peroxide, granules, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37

DCP-40MB-sl	Dicumyl peroxide, slabs, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-FF	Dicumyl peroxide, crystalline powder	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	5.86
BPDH	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane	2,5-二甲基-2,5-二(叔丁基过氧化)己烷	78-63-7	175	135	10.14
BPDH-40D-gr	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, granules, 40% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 细小颗粒,40%添加于中性填料中	78-63-7	175	135	4.41
BPDH-45B-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 粉料,45%添加于中性填料中	78-63-7	175	135	4.96
BPDH-45D-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 粉料,45%添加于中性填料中	78-63-7	175	135	4.96
BPDH-50D-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 50% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 粉料,50%添加于中性填料中	78-63-7	175	135	5.51
BPDH-3-45B-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexyne-3, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己炔-3 粉料,45%添加于中性填料中	1068-27-5	185	145	5.03
VA-40B-gr★	Butyl 4,4-di(tert-butylperoxy)valerate, granules, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯 细小颗粒,40%添加于中性填料中	995-33-5	160	125	3.83
VA-40B-pd★	Butyl 4,4-di(tert-butylperoxy)valerate, powder, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯 粉状,40%添加于中性填料中	995-33-5	160	125	3.83
VA-40MB-gr★	Butyl 4,4-di(tert-butylperoxy)valerate, granules, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯 细小颗粒,40%添加于中性填料中	995-33-5	160	125	3.83
VA-40MB-sl★	Butyl 4,4-di(tert-butylperoxy)valerate, slabs, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯 块状,40%添加于中性填料中	995-33-5	160	125	3.83
CH335-40B-gr	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, granules, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 细小颗粒,40%添加于中性填料中	6731-36-8	160	125	4.24
CH335-40B-pd	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, powder, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 粉状,40%添加于中性填料中	6731-36-8	160	125	4.24
CH335-40MB-gr	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, granules, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 细小颗粒,40%添加于中性填料中	6731-36-8	160	125	4.24
CH335-40MB-sl	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, slabs, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷 块状,40%添加于中性填料中	6731-36-8	145	115	4.24

TBPB	Tert-Butyl peroxybenzoate	过氧化苯甲酸叔丁酯	614-45-9	120	75	8.07
TBPB-50D-pd	Tert-Butyl peroxybenzoate, powder, 50% with inert fillers	过氧化苯甲酸叔丁酯 粉状,50%填充于中性填料中	614-45-9	140	100	4.12