

Cross-linking Peroxides / Wire and Cable

Product Name	Chemical Description	Chinese Name	Cas #	XL Temperature (°C)	Safe Processing Temperature (°C)	Active Oxygen
DPIB-40A-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% on EVA	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40B-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40B-gr-dd★	Di(tert-butylperoxyisopropyl)benzene, granules dedusted, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40B-pd★	Di(tert-butylperoxyisopropyl)benzene, powder, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 粉状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40K-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40K-pd★	Di(tert-butylperoxyisopropyl)benzene, powder, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 粉状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40MB-gr★	Di(tert-butylperoxyisopropyl)benzene, granules, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 细小颗粒,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIB-40MB-sl★	Di(tert-butylperoxyisopropyl)benzene, slabs, 40% with inert fillers	双(叔丁基过氧化异丙基)苯 块状,40%添加于中性填料中	25155-25-3	175	135	3.8
DPIBS-fl★	Di(tert-butylperoxyisopropyl)benzene, flakes	双(叔丁基过氧化异丙基)苯 片状	25155-25-3	175	135	9.08
DCP-40A-gr	Dicumyl peroxide, granules, 40% on EVA	二异丙苯过氧化物 细小颗粒,40%添加于EVA中	80-43-3	170	130	2.37
DCP-40B-gr-dd	Dicumyl peroxide, granules dedusted, 40% with inert fillers	二异丙苯过氧化物 细小脱尘颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40B-pd	Dicumyl peroxide, powder, 40% with inert fillers	二异丙苯过氧化物 粉状,40%添加于中性填料中	80-43-3	170	130	2.37

DCP-40K-gr	Dicumyl peroxide, granules, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40K-pd	Dicumyl peroxide, powder, 40% with inert fillers	二异丙苯过氧化物 粉状,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40MB-gr	Dicumyl peroxide, granules, 40% with inert fillers	二异丙苯过氧化物 细小颗粒,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40MB-sl	Dicumyl peroxide, slabs, 40% with inert fillers	二异丙苯过氧化物 块状,40%添加于中性填料中	80-43-3	170	130	2.37
DCP-40S-ps	Dicumyl peroxide, paste, 40% in silicone oil	二异丙苯过氧化物 糊状,40%添加于硅油中	80-43-3	170	130	2.37
DCP-FF	Dicumyl peroxide, crystalline powder	二异丙苯过氧化物 晶状粉末	80-43-3	170	130	5.86
BPO-50S-ps	Dibenzoyl peroxide, paste, 50% in silicone oil	二过氧化苯甲酰 糊状,50%溶于硅油中	94-36-0	105	85	3.31
LQ-DCBP-50S-ps	Di(2,4-dichlorobenzoyl) peroxide, paste, 50% in silicone oil	二(2,4-二氯苯甲酰)过氧化物 糊状,50%添加于硅油中	133-14-2	90	75	2.1
DMBP-50S-ps★	Di(4-methylbenzoyl) peroxide, paste, 50% in silicone oil	二(4-甲基苯甲酰)过氧化物 糊状,50%溶于硅油中	895-85-2	110	85	2.96
BPDH	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane	2,5-二甲基-2,5-二(叔丁基过氧化)己烷	78-63-7	175	135	10.14
BPDH-40D-gr	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, granules, 40% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 细小颗粒,40%添加于中性填料中	78-63-7	175	135	4.41
BPDH-45B-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 粉状,45%添加于中性填料中	78-63-7	175	135	4.96
BPDH-45D-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 粉状,45%添加于中性填料中	78-63-7	175	135	4.96
BPDH-45S-ps	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, paste, 45% in silicone oil	2,5-二甲基-2,5-二(叔丁基过氧化)己烷 糊状,45%添加于硅油中	78-63-7	175	135	4.96

BPDH-50D-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane, powder, 50% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己烷粉状,50%填充于中性填料中	78-63-7	175	135	5.51
BPYH-45B-pd	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexyne-3, powder, 45% with inert fillers	2,5-二甲基-2,5-二(叔丁基过氧化)己炔-3粉状,45%填充于中性填料中	1068-27-5	185	145	5.03
BPYH-E85	2,5-Dimethyl-2,5-di(tert-butylperoxy)hexyne-3, 85% solution in mineral oil	2,5-二甲基-2,5-二(叔丁基过氧化)己炔-3 85%溶于矿物油中	1068-27-5	185	145	9.5
VA-40B-gr★	Butyl 4,4-di(tert-butylperoxy)valerate, granules, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯细小颗粒,40%填充于中性填料中	995-33-5	160	125	3.83
VA-40B-pd★	Butyl 4,4-di(tert-butylperoxy)valerate, powder, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯粉状,40%填充于中性填料中	995-33-5	160	125	3.83
VA-40MB-gr★	Butyl 4,4-di(tert-butylperoxy)valerate, granules, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯细小颗粒,40%填充于中性填料中	995-33-5	160	125	3.83
VA-40MB-sl★	Butyl 4,4-di(tert-butylperoxy)valerate, slabs, 40% with inert fillers	4,4-二(叔丁基过氧化)戊酸丁酯块状,40%填充于中性填料中	995-33-5	160	125	3.83
CH335-40B-gr	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, granules, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷细小颗粒,40%填充于中性填料中	6731-36-8	160	125	4.24
CH335-40B-pd	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, powder, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷粉状,40%填充于中性填料中	6731-36-8	160	125	4.24
CH335-40MB-gr	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, granules, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷细小颗粒,40%填充于中性填料中	6731-36-8	160	125	4.24
CH335-40MB-sl	1,1-Di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, slabs, 40% with inert fillers	1,1-二(叔丁基过氧化)-3,3,5-三甲基环己烷块状,40%填充于中性填料中	6731-36-8	145	115	4.24
DTBP	Di-tert-butyl peroxide	叔丁基过氧化物	110-05-4	180	145	10.83
TBPB	tert-Butyl peroxybenzoate	过氧化苯甲酸叔丁酯	614-45-9	120	75	8.07
TBPB-50D-pd	tert-Butyl peroxybenzoate, powder, 50% with inert fillers	过氧化苯甲酸叔丁酯粉状,50%填充于中性填料中	614-45-9	140	100	4.12

TBCP★	tert-Butyl cumyl peroxide	叔丁基异丙基过氧化物	3457-61-2	175	135	7.3
TBCP-50D-pd★	tert-Butyl cumyl peroxide, powder, 50% with inert fillers	叔丁基异丙基过氧化物 粉状,50%添加于中性填料中	3457-61-2	175	135	3.84